

Always Reliable, Always Clear
And NOW SILKY SMOOTH

- High UV transmission
- Exceptional hiding power
- Excellent resistance to perspiration, dirt and bacteria
- Superior clean ability

Simply the best tanning bed shield material available!

Call your tanning distributor and ask for *Solaeryl* by name.



Spartech Polycast
Cell Cast Acrylic

SEE and FEEL the Beauty of Solaeryl Silk™

10,000 HOUR LIMITED WARRANTY

Spartech Polycast warrants that our SOLACRYL® SUVT acrylic sheet will transmit a minimum of 70 percent of available ultraviolet light measured at 340 nanometers for 10,000 hours under following conditions:

- Lamps used must be 85 to 100 watts maximum and have peak emission between 340 and 350 nanometers. (Examples: Sunlite F72-ST350-SM-85-100W and Instantan F72T12-ST350-HO)
- The minimum distance between the acrylic and the bulb is 7/8".
- The temperature between the acrylic and the bulb must not exceed 50°C.
- Sheet thickness must not be more than 3/16".

Light transmission value at 340 nanometers will be determined by standard spectrophotometric techniques on a thoroughly cleaned sample.

This warranty does not cover loss of ultraviolet light transmission caused by yellowing, crazing, scratches, dirt, breakage, or other damage. Furthermore, this warranty does not cover damage to the sheet as a result of stains caused by the use of inappropriate chemicals, including oils, lotions, creams, cosmetics, cleaners, and disinfectants. A list of appropriate cleaners and disinfectants may be obtained from your local SOLACRYL SUVT sheet distributor, or directly from Spartech Polycast, 70 Carlisle Place, Stamford, CT 06902; (800) 243-9002.

THE FOREGOING IS OUR SOLE WARRANTY FOR SOLACRYL® SUVT ACRYLIC SHEET. WE HEREBY DISCLAIM ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, WITHOUT LIMITATIONS, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

The warranty covers only the light transmission of SOLACRYL SUVT acrylic sheet under the conditions set forth above. Furthermore, there is no warranty or liability for crazing of the sheet. Spartech Polycast assumes no responsibility for the use of the SOLACRYL SUVT sheet, nor for the health and safety of any person who comes in contact with this product. Since the application and conditions of use are beyond Spartech Polycast's control, the user is solely responsible to determine the suitability of the product for the user's specific application.

THE SOLE LIABILITY OF SPARTECH POLYCAST IN THE EVENT OF ANY BREACH OF THE FOREGOING WARRANTY WILL BE TO REPLACE ANY SOLACRYL SUVT SHEET. Spartech Polycast reserves the right either to replace the sheet or to provide a refund at current prices. In addition, Spartech Polycast assumes no responsibility for any costs incurred in removing defective sheet or installing a replacement, nor for any damage to persons or to property, nor for any indirect, incidental, or consequential damages.

Any person making a claim in connection with this warranty should contact Spartech Polycast, 70 Carlisle Place, Stamford, CT 06902, or the nearest SOLACRYL SUVT acrylic sheet distributor. A Spartech Polycast representative will contact you to arrange for inspection of the sheet. At the time of inspection, we will need evidence that shows the purchase date of the sheet and when it went into service.

Some states do not permit the exclusion or limitation of incidental and consequential damages. The foregoing warranty gives you specific legal rights, and you may also have other rights which vary from state to state.



TYPICAL PHYSICAL PROPERTIES OF SOLACRYLTM ACRYLIC SHEET

| Property(1) | Value | Test Method |
|---|----------|-------------|
| Modulus of Elasticity, psi | 400,000 | ASTM D638 |
| Tensile Strength (Rupture), psi | 8600 | ASTM D638 |
| Elongation Rupture, % | 6-8 | ASTM D638 |
| Specific Gravity | 1.19 | ASTM D792 |
| Residual Shrinkage, % | 2.2 | ASTM D4802 |
| Refractive Index | 1.49 | ASTM D542 |
| Total Luminous Transmittance (as-cast), % | 88 | ASTM D1003 |
| Hot Forming Temperature, °F | 290-330 | |
| Heat Distortion Temperature, °F | 264 | ASTM D648 |
| Maximum Continuous Service Temperature, °F | 140-170 | |
| Coefficient of Linear Thermal Expansion, in/in/°F | 0.000042 | ASTM D696 |
| Flammability, in/min | 1.1-1.3 | ASTM D635 |
| UL Flame Class | 94 HB | UL |
| Self-Ignition Temperature, °F | 800-860 | ASTM D1929 |
| Plastic Component | Listed | UL 746C |

(1) Tests conducted on material 0.187 in. thick (average value).

NOTE: These data are typical sheet properties and are not intended for specification purposes. They are the latest at the time of publication and are authentic to the best knowledge of the company. The properties are listed solely to give general guidance and are not to be construed as a warranty of any type. Please contact Spartech Polycast for specific data to meet your design criteria.



ISO 9001:2000
FM 76298

www.spartech.com
polycast.marketing@spartech.com



Spartech Polycast
Cell Cast Acrylic

70 Carlisle Place, Stamford CT 06902
203-327-6010 FAX: 203-323-2925 (International)
800-243-9002 FAX: 800-631-4005