



Polycast® Acryshield® Bullet Resistant Sheet

Polycast® Acryshield® Bullet Resistant sheet is an effective solution for essential barrier protection in glazing applications. The different available grades are UL designated and are designed to fit a variety of ballistic protection applications.

The characteristics most often considered when choosing a bullet resistant sheet are adequate protection, weight, optical clarity and cost. Polycast® Acryshield® bullet resistant sheet offers the right balance of properties to meet these specific protection needs. Lighter weight than glass, and with superior optical clarity, Polycast® Acryshield® bullet resistant sheet is a clear choice for ballistic protection.

KEY CHARACTERISTICS

- **Lighter weight**—weighs 48% less than glass with the same UL rating, and less than polycarbonate sheet offering the same protection
- **Optical clarity**—transmits more light than bullet resistant glass or polycarbonate
- **Design flexibility**—can be cut to any size using standard tools without chipping or cracking, and can be formed into curved shapes and polished to a clear luster; color and tint options also available

- **Long-lasting appeal**—maintains beauty over time; will not turn yellow, haze, degrade or turn brittle when exposed to the elements
- **Abrasion resistance**—available with a super abrasion resistant (SAR) coating that can maintain 45 times the abrasion resistance of uncoated acrylic

MARKET AND APPLICATIONS

Polycast® Acryshield® bullet resistant sheet is effective for use in many environments, including:

- Retail storefronts such as banks, convenience stores, pharmacies or jewelry stores
- School buildings
- Residential or office buildings
- Government buildings and embassies
- Armored vehicles, both military and civilian

Call 800-677-4338 or email marketing@spartech.com to order these products.

FOLLOW US:

Available Grades

UL 752 Ballistic Standards



Acryshield® MP1.25, SARMP1.25

Protects against handguns of medium power, such as the 9mm and Super 38 Automatics – any handgun with a muzzle energy of 380 to 460 foot-pounds.

Acryshield® HP1.25, SARHP1.25

Thin, light protection against high-power handguns, such as the .357 Magnum or other guns with a muzzle energy of 548 to 663 foot-pounds. **NOTE:** SARHP1.25 UL 752 Ballistic is not certified for outdoor applications.

Acryshield® SP1.25

Ballistics protection against all handguns, including super power guns such as the .44 Magnum. Exceeds criteria within UL Level 3 requirements.

Acryshield® SMG1.25

Multiple shot protection from a submachine gun, such as a 9mm Uzi, and exceeding criteria within UL Level 6 requirements.

TECHNICAL PROPERTIES

	ACRYSHIELD® MP1.25, SARMP1.25 (UL 752 Level 1)	ACRYSHIELD® HP1.25 (UL 752 Level 2)	ACRYSHIELD® SARHP1.25 (UL 752 Level 2)	ACRYSHIELD® SP1.25 (UL 752 Level 3)	ACRYSHIELD® SMG1.25 (UL 752 Level 6)
Protection	9 mm	.357 Magnum	.357 Magnum	.44 Magnum	Submachine Gun / Uzi
Optical Properties	Transmission > 90% Haze < 1%	Transmission > 90% Haze < 1%	Transmission > 90% Haze < 1%	Transmission > 85% Haze < 1.5%	Transmission > 85% Haze < 1.5%
UL Designation	752, Level 1	752, Level 2	752, Level 2	752, Level 3	752, Level 6
Thickness	1.25"	1.378"	1.378"	1.25"	1.25"
Weight	7.7 lbs. / sq. ft.	8.5 lbs. / sq. ft.	8.5 lbs. / sq. ft.	7.7 lbs. / sq. ft.	7.7 lbs. / sq. ft.
SAR Coating	Optional	N/A	Standard	Standard	Standard
UL Indoor/Outdoor Application Rating	Indoor/Outdoor	Indoor/Outdoor	Indoor Only	Indoor/Outdoor	Indoor/Outdoor

AVAILABLE SIZES

MP1.25 LEVEL 1			HP1.25 LEVEL 2			SP1.25 LEVEL 3			SMG 1.25 LEVEL 6		
4' x 6'	5' x 6'	6' x 8'	4' x 6'	5' x 6'	6' x 8'	4' x 6'	5' x 6'	6' x 8'	4' x 6'	5' x 6'	6' x 8'
4' x 8'	5' x 8'	6' x 10'	4' x 8'	5' x 8'	6' x 10'	4' x 8'	5' x 8'	6' x 10'	4' x 8'	5' x 8'	6' x 10'

Code ratings and Standards:

Meets the test requirements of Building Code class CC2, ANS, Z97.1-Safety Glazing Material, ANS, Z26.1-Motor Vehicle Safety Glazing Material, Federal Specification L-P-391D+ ASTM D 4802.

Continuous Service Temperatures for SARHP1.25:

Maximum 95° F, Minimum 55° F

All Other Levels:

Maximum Continuous Service Temperature:

170° F

Minimum Continuous Service Temperature:

-26° F (lowest temperature tested for bullet-resistance)

11650 Lakeside Crossing Ct. • Maryland Heights, MO 63146 • 800-677-4338 • www.spartech.com

Copyright ©2026. This information reflects estimates that may be affected by a variety of factors and are not guarantees or minimum or maximum values. Spartech is not responsible for testing, product selection and suitability, handling, and fitness for use determinations. SPARTECH MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All sales are subject to our terms and conditions (<https://www.spartech.com/resources-bin/terms-and-conditions>).