

WeatherPro LG

Product Description

Low Gloss weatherable sheet

Technical Properties

Property	Test Method	Value
Specific Gravity	ASTM D-792	1.079
Melt flow rate (230C/3.8kg)	ASTM D-1238	1.57 g/10min
Tensile Strength	ASTM D-638	5400 PSI
Tensile Elongation at yield	ASTM D-638	3%
Tensile elongation at Break	ASTM D-638	48%
Flex strength	ASTM D-790	8000 PSI
Flex Modulus	ASTM D790	270000 Psi
Notched Izod at 73F	ASTM D-256	3.5 ft-lb/in
Heat Deflection Temperature at 264 psi	ASTM D-648	197 F
Vicat softening temperature	ASTM D-1525	221 F
CLTE	ASTM E-831	6.5 E-5 in/in/F
Gloss	ASTM D-2457	14

**All values based on 0.125" unless otherwise stated*

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail info@spartech.com or visit our website at www.spartech.com

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. **NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**